



## Product Data

<b>Water permeability</b>	0.25 ml.m.day	<b>LOW</b>	tested at 28 days
<b>Vapour permeability</b>	0.75 gr.m <sup>2</sup> .hour.mmHg	<b>VERY HIGH</b>	tested at 28 days

	<b>Tensile Strength</b> N/mm <sup>2</sup>	<b>Compressive Strength</b> N/mm <sup>2</sup>	<b>Elasticity Moduli</b> MPa	<b>Shrinkage</b> mm.m
7 days	2.20	6.20		0.81
28 days	2.38	7.25	7690	0.85

See our [Copyright and Disclaimer Statement](#)